

**Features**

- Ultra realistic looks with matte finishes and painted bevels
- High-density core delivers enhanced dimensional stability, outstanding indentation resistance, and is impervious to water damage
- The collection qualifies for the 3-Season Warranty, please refer to installation instructions for more detail



**Product Information**

<b>Product Line</b>	Wishone Luxury Vinyl Flooring
<b>Construction</b>	SPC (Stone Polymer Composite) vinyl
<b>Dimension</b>	6mm (T) x 146mm (W) x 730mm (L)
<b>Underlayment</b>	1.5mm cork underlayment
<b>Wear Layer Thickness</b>	0.5mm (20 mil)
<b>Finish</b>	2-pass UV cured Urethane Finish
<b>Installation</b>	Floating installation by clicking the end joints together. Please refer to Installation Instruction
<b>Warranty</b>	30 Year Residential and 12 Year Commercial Warranty

**Testing**

Classification	Method	Result
Class	ASTM F1700	Class III, Type B - Embossed
Slip Resistance	ASTM C1028-07	Dry: 0.80; Wet: 0.71
Static Load	ASTM F970	Applied Load: 1000 psi, Residual Indentation: 0.04mm
Impact Isolation Class	ASTM E492-09	71
Sound Transmission Class	ASTM E90-09	71
Dimensional Stability	ASTM F2199	Pass: ≤0.02 in. per linear foot
Resistant to Chemicals	ASTM F925	Pass: Not affected
Abrasion	ASTM D4060	Test Revolutions: 1000, 0.004% mass loss
Antibacterial Activity	ASTM G21-15	Pass: No growth observed on specimens
Reaction to Fire	EN13501-1	Class B fl-s1
Critical Radiant Flux	ASTM E648	Pass, >0.45 watts/cm <sup>2</sup>
Concentration of Dibutyl Phthalate	ISO 16000	<1 µg/m <sup>3</sup> after 28 days
Concentration of Diethylhexyl Phthalate	ISO 16000	<1 µg/m <sup>3</sup> after 28 days
Flexibility	EN435	No Damage

**Packaging Information**

	Length (mm)	Width (mm)	Thickness (mm)	Sq. ft. per Carton	Weight (lb. per carton)
<b>Carton</b>	735	110	150	20.7	40

**Pallet Information**

	Length (mm)	Width (mm)	Height (mm)	Volume (m <sup>3</sup> )	# of carton per Pallet	Sq. ft. /pallet	Weight (lb.)
<b>Plank Pallet</b>	740	910	1300	0.88	48	993.6	1920